Matrixx F663E33

Polyamide 66

The Matrixx Group, Inc.

Message:

Matrixx F663E33 is a polyamide 66 (nylon 66) material, which contains a 33% glass fiber reinforced material. This product is available in North America and is processed by injection molding. The main characteristics of Matrixx F663E33 are: flame retardant/rated flame.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 33% filler by weight		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10 - 0.40	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	190	MPa	ASTM D638
Flexural Modulus - Tangent	8620	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	100	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	249	°C	ASTM D648
RTI	65.6	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	НВ		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	71.1 - 93.3	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	271 - 299	°C	
Middle Temperature	271 - 299	°C	
Front Temperature	271 - 299	°C	
Processing (Melt) Temp	277 - 299	°C	
Mold Temperature	65.6 - 93.3	°C	
Injection Rate	Moderate-Fast		
Back Pressure	< 0.345	MPa	
Cushion	6.35 - 12.7	mm	
Injection instructions			

Dessicant dryer with -20°F dewpointScrew Speed: Slow to Medium

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

