

Durethan® AKV 30 G H2.0 SR1 900051

Polyamide 66

LANXESS GmbH

Message:

PA 66, 30 % glass fibers, injection molding, heat-aging stabilized, improved surface finish

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Heat Stabilizer		
Features		Good Surface Finish		
		Heat Stabilized		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.36	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Across Flow : 280°C, 3.00 mm ¹	0.94	--	%	
Across Flow : 120°C, 4 hr, 3.00 mm ²	0.080	--	%	
Flow : 280°C, 3.00 mm ³	0.25	--	%	
Flow : 120°C, 4 hr, 3.00 mm ⁴	0.040	--	%	
Water Absorption				ISO 62
Saturation, 23°C	6.0	--	%	
Equilibrium, 23°C, 50% RH	2.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	220	120	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9600	6500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	180	120	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	6.0	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	8400	5600	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain,23°C	260	150	MPa	
23°C ⁶	270	170	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	6.0	%	ISO 178/A
Burning Behavior ⁸	passed	--		ISO 3795
ISO Shortname	PA 66, GHR, 14-100, GF30	--		ISO 1874

Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°C	< 10	< 10	kJ/m ²	
-30°C	< 10	< 10	kJ/m ²	
23°C	10	15	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	60	kJ/m ²	
23°C	70	75	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	
23°C	< 10	< 10	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	50	50	kJ/m ²	
23°C	55	65	kJ/m ²	
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	1.90	--	J	
23°C	2.10	3.60	J	
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	680	--	N	
23°C	740	920	N	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	250	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	220	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	90.0	--	°C	ISO 75-2/C
Vicat Softening Temperature	> 230	--	°C	ISO 306/B50, ISO 306/B120
Melting Temperature ⁹	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	2.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	9.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+12	ohms · cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	31	28	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250

23°C, 100 Hz	4.00	8.00		
23°C, 1 MHz	4.00	4.00		
Dissipation Factor				IEC 60250
23°C, 100 Hz	9.0E-3	0.18		
23°C, 1 MHz	0.017	0.060		
Comparative Tracking Index (Solution A)	375	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		
3.20 mm	HB	--		
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index ¹⁰	26	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	280 to 300		°C	
Mold Temperature	80.0 to 120		°C	
NOTE				

- | | |
|-----|-------------------------------|
| 1. | 150x105x3mm, 80°C MT, 500 bar |
| 2. | 150x105x3mm |
| 3. | 150x105x3mm, 80°C MT, 500 bar |
| 4. | 150x105x3mm |
| 5. | 2.0 mm/min |
| 6. | 2.0 mm/min |
| 7. | 2 mm/min |
| 8. | US-FMVSS302 |
| 9. | 10°C/min |
| 10. | Procedure A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT