

InnoFR™ FX-8061

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

Message:

FX-8061 is a flexible polyurethane formulated for room temperature hand-batch systems. Excellent physical properties can be obtained without the utilization of mercury, MOCA, or TDI. FX-8061 meets the criteria to pass UL 94VO.

General Information			
Features	Flame Retardant		
	Good Flexibility		
Appearance	White		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
Hardener	1.21	g/cm ³	
Cured	1.28	g/cm ³	
Base Resin	1.30	g/cm ³	
Molding Shrinkage - Flow	0.10 to 0.50	%	ASTM D2566
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 100		
Hardener	Mix Ratio by Weight: 100		
	Mix Ratio by Weight: 36		
Resin	Mix Ratio by Volume: 33		
Demold Time	120 to 240	min	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity			
25°C ¹	0.32	Pa · s	
25°C ²	1.3	Pa · s	
25°C ³	1.3	Pa · s	
Curing Time (25°C)	1.7E+2	hr	
Gel Time	10 to 15	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	55 to 65		ASTM D2240
Tensile Strength	3.62	MPa	ASTM D638
Tensile Elongation at Break	180	%	ASTM D638

Tear Strength	13.1	kN/m	ASTM D624
NOTE			
1.	Resin		
2.	Mixed		
3.	Hardener		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

