Borealis PE PC0787

Polyethylene

Borealis AG

Message:

PC0787 is a flame retardant crosslinking polyethylene compound for low voltage insulation.

PC0787 contains flame retardant additives to reduce normal flame spread characteristics so as to achieve a VW-1 flame resistance rating when tested according to the UL 44 Vertical Flame test on 14 AWG/45Mils wires. PC0787 contains a slower peroxide and therefore provides wider processing latitude. It is recommended for control cable insulation.

General Information			
Features	Crosslinkable		
	Flame Retardant		
Uses	Wire & Cable Applications		
Agency Ratings	UL 44		
	UL 854		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.22	g/cm³	ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	13.1	MPa	ASTM D412
Tensile Elongation (Break)	280	%	ASTM D412
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (150 168 hr))°C, > 10	%	ASTM D573
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	> 22	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	2.75		ASTM D150
Dissipation Factor (60 Hz)	2.6E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	27	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	240	°C	
Cylinder Zone 2 Temp.	250	°C	
NOTE			
1.	Compound		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

