

NYLOY® MS-0100B-13

Polyamide 66

Nytex Composites Co., Ltd.

Message:

NYLOY® MS-0100B-13 is a Polyamide 66 (Nylon 66) material. It is available in Asia Pacific or North America for injection molding. Primary attribute of NYLOY® MS-0100B-13: Impact Modified.

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	0.916	g/cm ³	ASTM D792
--	1.07	g/cm ³	ISO 1183
Molding Shrinkage			ASTM D955, ISO 294-4
Flow	1.7	%	
Across Flow	1.7	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	72		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	36.8	MPa	ASTM D638
--	36.0	MPa	ISO 527-2
Tensile Elongation			
Break	140	%	ASTM D638
Break	130	%	ISO 527-2
Flexural Modulus			
--	1410	MPa	ASTM D790
--	1200	MPa	ISO 178
Flexural Strength			
--	52.0	MPa	ASTM D790
--	46.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	77	kJ/m ²	
23°C	90	kJ/m ²	
Notched Izod Impact			ASTM D256
-20°C, 3.18 mm	690	J/m	

23°C, 3.18 mm	980	J/m
Injection	Nominal Value	Unit
Drying Temperature	110	°C
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

