# BorPEX™ HE2550

### High Density (HMW) Polyethylene

#### Borealis AG

#### Message:

BorPEX HE2550 is a high molecular weight, high density polyethylene specially designed for production of crosslinked pipes (PE-X).

BorPEX HE2550 is intended to fulfill following standards and regulations, in case of appropriate industrial manufacturing standard procedures applied and a continuous quality system is implemented.

DIN 16892

DIN 16893

EN ISO 15875

**ASTM F 876** 

BorPEX HE2550 is a free flowing powder for the PE-Xa, peroxide crosslinking process. The material is only stabilized for transporting and storage. Crosslinking agent (e.g. peroxide) and stabilisers have to be added by the pipe manufacturer. Good crosslink response and well-balanced powder size distribution enable effective soaking and a stable pipe production.

General Information			
Additive	Unspecified Stabilizer		
Features	Clean/High Purity		
	Crosslinkable		
	Good Processability		
	Good Stability		
	High Molecular Weight		
Uses	Industrial Applications		
	Piping		
	Plumbing Parts		
Agency Ratings	ASTM F 876		
	DIN 16892		
	DIN 16893		
	ISO 15875		
Forms	Powder		
Processing Method	Extrusion		
	Pipe Extrusion		
Physical	Nominal Value	Unit	Test Method
Density <sup>1</sup>	0.956	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	6.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	22.0	MPa	ISO 527-2/50
Tensile Strain (Break)	600	%	ISO 527-2

NOTE

1. Base resin

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

