

# CoREZYN® COR30-DZ-204

Thermoset Polyester

Interplastic Corporation

## Message:

CoREZYN also supplies isophthalic and orthophthalic polyester resins for applications used in less severe environments. End-use applications include beams, pipes, channels, tubing and more.

General Information		
Features	Good Corrosion Resistance	
	Isophthalic	
	Low Viscosity	
	Medium Reactivity	
Uses	Piping	
	Tubing	
Additional Information	Nominal Value	Unit
Gel to Peak	1.0 to 3.0	min
Non-Volatile Content	58 to 63	%
Peak Exotherm	204 to 232	°C
Uncured Properties	Nominal Value	Unit
Viscosity (25°C, Brookfield HBT)	0.50 to 0.90	Pa·s
Gel Time <sup>1</sup>	4.5 to 7.5	min
NOTE		

1.

SPI gel time run in 180°F (82°C)  
water bath, catalyzed with 1.0 phr  
of 98% benzyol peroxide, minutes.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT