

Rilsan® BECV0 P40 TL

Polyamide 11

Arkema

Message:

Rilsan® BECV0 P40 TL is a Polyamide 11 (Nylon 11) product. It can be processed by extrusion and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

- Eco-Friendly/Green
- Good UV Resistance
- Heat Stabilizer
- High Viscosity
- Plasticized

General Information			
Additive	Heat Stabilizer		
	UV Stabilizer		
Features	Good UV Resistance		
	Heat Stabilized		
	High Viscosity		
	Plasticized		
	Renewable Resource Content		
Appearance	Natural Color		
Forms	Pellets		
	Powder		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Water Absorption			ASTM D570
24 hr	0.30	%	
Saturation	1.0	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	78		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	63.4	MPa	ASTM D638
Tensile Elongation (Break)	360	%	ASTM D638
Flexural Modulus	310	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	16	J/m	

23°C	430	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	41.1	°C	ASTM D648
Melting Temperature	186	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

