

SABIC® HDPE M453SG

High Density Polyethylene Copolymer

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® HDPE M453SG is typically used for the high demanding dustbin market. It is an UV stabilized HDPE copolymer grade. It typically shows a good combination of processability, consistency and product properties, good stiffness/cold impact-balance, surface quality and weatherability properties. Typical applications.

SABIC® HDPE M453SG is typically used for the manufacture of injection molded dustbins (waste containers on wheels and household containers), crates & boxes (pallet boxes, pallets, boxes applied at low temperatures) and pails & container applications (industrial, shipping).

This product is not intended for and must not be used in any pharmaceutical/medical applications.

General Information			
Additive	UV stabilizer		
Features	UV Stabilized		
	Rigid, good		
	High density		
	Copolymer		
	Workability, good		
	Low temperature impact resistance		
	Good weather resistance		
Uses	Excellent appearance		
	Pallets		
	Waste container		
	Industrial container		
	Household goods		
	Barrel		
	Loading box		
Processing Method	Shipping container		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.953	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	4.0	g/10 min	ISO 1133
190°C/5.0 kg	11	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	61		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (2.00 mm, Compression Molded)	1100	MPa	ISO 527-2/1BA/50

Tensile Stress			ISO 527-2/1BA/50
Yield, 2.00mm, molded	26.0	MPa	ISO 527-2/1BA/50
Fracture, 2.00mm, molded	31.0	MPa	ISO 527-2/1BA/50
Tensile Strain (Break, 2.00 mm, Compression Molded)	> 200	%	ISO 527-2/1BA/50
Flexural Modulus (2.00 mm, Compression Molded)	1200	MPa	ISO 178
Flexural Stress (2.00 mm, Compression Molded)	26.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Compression Molded)	5.0	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	81.0	°C	ISO 75-2/B
Vicat Softening Temperature	124	°C	ISO 306/A
Melting Temperature (DSC)	132	°C	ISO 11357-3
Enthalpy Change	203	J/g	ISO 11357-3
Injection	Nominal Value	Unit	
Processing (Melt) Temp	232 - 260	°C	
Mold Temperature	20 - 40	°C	
Injection Pressure	93.0 - 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

