NEFTEKHIM PE 4020W (20425)

Linear Low Density Polyethylene

Nizhnekamskneftekhim Inc.

Message:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts.

Stabilization recipe: antacid, antioxidant, thermostabilizer, processing aid, dispersing agent...

Application: general purpose, injection molding of pails and containers.

Technical requirements: TU 2211-145-05766801-2008

General Information			
Additive	Acid Neutralizer		
	Antioxidant		
	Heat Stabilizer		
	Processing Aid		
Features	Acid Resistant		
	Antioxidant		
	Dispersible		
	Good Processability		
	Heat Stabilized		
Uses	Containers		
	General Purpose		
	Pails		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.918 to 0.920	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16	22 += 20	a /10 min	ACTM D1220
kg)	22 to 28	g/10 min	ASTM D1238
Melt Flow Ratio - MFR 21.6 kg/MFR 2.16 kg	< 30.0		ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	400	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

