Wanthane® WHT-1685AD

Thermoplastic Polyurethane Elastomer (Polyester)

Wanhua Chemical Group Co., Ltd.

Message:

WHT-1685AD is polyester-based TPU for extrusion molding applications, supplied in form of transparent, translucent, colorless or slightly yellowish film with good workability for high frequency soldering.

Applications:

Package, Exterior Decoration Parts, Fabric Coating.

General Information				
Uses	Packaging			
	Coating application			
	Fabric			
	Decorative parts			
Appearance	Translucent			
	Transparent-Slightly Yellow			
	Colorless			
Forms	Films			
Processing Method	Extrusion			
Physical	Nominal Value	Unit	Test Method	
Density	1.19	g/cm³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	85		ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress			ASTM D412	
100% strain	5.00	МРа	ASTM D412	
300% strain	7.00	МРа	ASTM D412	
Tensile Strength	15.0	МРа	ASTM D412	
Tensile Elongation (Break)	690	%	ASTM D412	
Tear Strength	65.0	kN/m	ASTM D624	
Thermal	Nominal Value	Unit	Test Method	
Glass Transition Temperature	-40.0	°C	ASTM D3417	
Optical	Nominal Value	Unit	Test Method	
Transmittance	89.0	%	ASTM D1003	
Extrusion	Nominal Value	Unit		
Drying Temperature	80.0 - 110	°C		
Drying Time	2.0 - 3.0	hr		
Cylinder Zone 1 Temp.	165	°C		
		°C		

Cylinder Zone 3 Temp.	175	°C	
Cylinder Zone 4 Temp.	180	°C	
Cylinder Zone 5 Temp.	180 - 185	°C	
Extrusion instructions			

Extruder Feed Section: 160

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

