

# AURUM® JCF3030

Thermoplastic Polyimide

Mitsui Chemicals, Inc.

## Message:

Features  
Carbon Fiber Reinforced, Wear Resistance  
High Strength, High Modulus

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Features	High strength		
	Good wear resistance		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage			Internal method
Flow	0.0	%	Internal method
Transverse flow	0.70	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	195	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	14200	MPa	ASTM D790
Flexural Strength	276	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	246	°C	ASTM D648
Linear thermal expansion coefficient			ASTM D696
Flow	6.0E-6	cm/cm/°C	ASTM D696
Lateral	4.5E-5	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

