

GPPS Microgranulates 130M

General Purpose Polystyrene
INEOS Styrenics International SA

Message:

130M is a general purpose polystyrene grade with excellent flow properties and has a high surface to volume rate.

General Information			
Features	Food Contact Acceptable		
	General Purpose		
	Good Flow		
Uses	General Purpose		
	Masterbatch		
Agency Ratings	EU 10/2011		
RoHS Compliance	Contact Manufacturer		
Forms	Microgranules		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (200°C/5.0 kg)	25.0	cm ³ /10min	ISO 1133
Molding Shrinkage	0.30 to 0.60	%	ISO 294-4
Water Absorption (23°C, 24 hr)	< 0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3300	MPa	ISO 527-2/1
Tensile Stress (Break)	45.0	MPa	ISO 527-2/50
Nominal Tensile Strain at Break	2.0	%	ISO 527-2/50
Flexural Stress ¹	61.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	10	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	75.0	°C	ISO 75-2/A
Vicat Softening Temperature	85.0	°C	ISO 306/B50
CLTE - Flow (23 to 80°C)	8.0E-5	cm/cm/°C	DIN 53752
Thermal Conductivity	0.16	W/m/K	DIN 52612
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT