

PENTAMID A GV30 HYD RC schwarz

Polyamide 66

PENTAC Polymer GmbH

Message:

Normal viscosity, heat and hydrolysis stabilised polyamide 66, 30% glass fiber reinforced

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Heat Stabilizer		
		Hydrolysis Resistant		
Recycled Content		Yes		
Features		Heat Stabilized		
Uses		Housings		
Agency Ratings		EC 1907/2006 (REACH)		
Appearance		Black		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.80	--	%	
Flow	0.50	--	%	
Water Absorption				ISO 62
Saturation, 23°C	5.0	--	%	
Equilibrium, 23°C, 50% RH	1.5	--	%	
Viscosity Number	135	--	cm ³ /g	ISO 307
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 961/30)	240	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	8400	6700	MPa	ISO 527-2/1
Tensile Stress (Break)	165	115	MPa	ISO 527-2
Tensile Strain (Break)	4.0	5.0	%	ISO 527-2
Flexural Modulus	7900	--	MPa	ISO 178
Flexural Stress	220	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	70	85	kJ/m ²	ISO 179/1eU

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	255	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	240	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength (1.00 mm)	35	--	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	3.50	--		IEC 60250
Comparative Tracking Index	400	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		
3.20 mm	HB	--		
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA66, MHWRC, 14-080, GF30	PA66, MHWRC, 14-080, GF30		ISO 1874
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	3.0		hr	
Suggested Max Moisture	0.090		%	
Suggested Max Regrind	20		%	
Rear Temperature	265 to 290		°C	
Middle Temperature	280 to 295		°C	
Front Temperature	280 to 290		°C	
Processing (Melt) Temp	285		°C	
Mold Temperature	80.0		°C	
Injection Pressure	78.0		MPa	
Holding Pressure	46.8		MPa	
Screw L/D Ratio	20.0:1.0			
Screw Compression Ratio	2.2:1.0 to 2.8:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT