

PRL NY6-M40

Polyamide 6
Polymer Resources Ltd.

Message:

PRL NY6-M40 is a Polyamide 6 (Nylon 6) product filled with 40% mineral. It can be processed by injection molding and is available in North America. Characteristics include:
RoHS Compliant
Lubricated

General Information			
Filler / Reinforcement	Mineral,40% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.49	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.70 to 1.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	89.6	MPa	
Break, 3.18 mm	89.6	MPa	
Flexural Modulus (3.18 mm)	5860	MPa	ASTM D790
Flexural Strength (3.18 mm)	128	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	166	°C	
1.8 MPa, Unannealed, 3.18 mm	120	°C	
Injection	Nominal Value	Unit	
Drying Temperature	73.9 to 85.0	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	232 to 249	°C	
Middle Temperature	243 to 260	°C	
Front Temperature	249 to 268	°C	
Processing (Melt) Temp	249 to 271	°C	
Mold Temperature	82.2 to 104	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

