

ELEVATE™ EF575

Ethylene Vinyl Acetate Copolymer

Westlake Chemical Corporation

Message:

Westlake EF575AA resin is a fractional melt index 7.5% EVA copolymer designed for ice bags, frozen food bags, and other films that require excellent toughness and good heat sealing characteristics. This Kosher compliant resin has excellent low temperature brittleness properties.

- Application/Uses:
- Frozen food packaging
 - Fresh food packaging
 - Ice bags
 - Heavy duty produce bags

General Information			
Features	Kosher certification		
	Copolymer		
	Good heat sealability		
	Low temperature resistance		
	Good toughness		
Uses	Packaging		
	Bags		
	Food packaging		
Agency Ratings	FDA 21 CFR 177.1350		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.929	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)	0.55	g/10 min	ASTM D1238
Vinyl Acetate Content	7.5	wt%	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	32	µm	
secant modulus			ASTM D882
1% secant, MD: 32 µm, blown film	103	MPa	ASTM D882
1% secant, TD: 32 µm, blown film	110	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Broken, 32 µm, blown film	24.1	MPa	ASTM D882
TD: Broken, 32 µm, blown film	25.5	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 32 µm, blown film	380	%	ASTM D882
TD: Broken, 32 µm, blown film	550	%	ASTM D882
Dart Drop Impact (32 µm, Blown Film)	480	g	ASTM D1709
Optical	Nominal Value	Unit	Test Method

Gloss (45°, 31.8 µm, Blown Film)	74		ASTM D2457
Haze (31.8 µm, Blown Film)	4.8	%	ASTM D1003
Additional Information	Nominal Value	Unit	
Blown Film Melt Temperature ¹	182 - 204	°C	

Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity. Test specimens for blown film: nominal thickness 1.25 mils; blow up ratio 2.5:1, die gap 35 mils.

NOTE

1. Temperature recommended for Westlake Chemical EF575 with blow-up ratios of 1.5:1 or higher.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

