

LinGen FR295

Thermoplastic Elastomer
Shanghai Lin Gen Rubber Materials Co., Ltd.

Message:

LinGen FR295 is a thermoplastic elastomer (TPE) material. This product is available in the Asia-Pacific region and is processed by extrusion or injection molding.

The main features of LinGen FR295 are:

Flame Retardant

Halogen-free

General Information	
Features	Halogen-free
	Flame retardancy

Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Specific Gravity	1.20	g/cm ³	ASTM D792
------------------	------	-------------------	-----------

Hardness	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Durometer Hardness (Shore D)	40		ASTM D2240
------------------------------	----	--	------------

Elastomers	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Tensile Strength (Yield)	23.0	MPa	ASTM D412
--------------------------	------	-----	-----------

Tensile Elongation (Break)	380	%	ASTM D412
----------------------------	-----	---	-----------

Aging	Nominal Value	Unit	
-------	---------------	------	--

Change in Tensile Strength (135°C, 168 hr)	-20	%	
--	-----	---	--

Change in Ultimate Elongation (135°C, 168 hr)	-20	%	
---	-----	---	--

Electrical	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Surface Resistivity	> 1.0E+12	ohms	ASTM D257
---------------------	-----------	------	-----------

Dielectric Strength	24	kV/mm	ASTM D149
---------------------	----	-------	-----------

Dielectric Constant (1 MHz)	5.20		ASTM D150
-----------------------------	------	--	-----------

Dissipation Factor (1 MHz)	0.050		ASTM D150
----------------------------	-------	--	-----------

Injection	Nominal Value	Unit	
-----------	---------------	------	--

Drying Temperature	70 - 80	°C	
--------------------	---------	----	--

Drying Time	4.0 - 8.0	hr	
-------------	-----------	----	--

Processing (Melt) Temp	190 - 240	°C	
------------------------	-----------	----	--

Injection Pressure	40.0 - 60.0	MPa	
--------------------	-------------	-----	--

Extrusion	Nominal Value	Unit	
-----------	---------------	------	--

Melt Temperature	180 - 230	°C	
------------------	-----------	----	--

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHEG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

