KOPELEN B-310

Polypropylene Impact Copolymer

Lotte Chemical Corporation

Message:

B-310 is impact block copolymer which has ethylene-propylene rubber inside homo polypropylene.This grade can be processed by sheet extrusion. B-310 shows good impact resistance at low temperature and has also high strength.It has good vacuum molding property, suitable for the production of vacuum molding goods.B-310 is applied to food packaging tray, various industrial sheets.

| General Information | | | | | |
|---------------------------------------|-----------------------------------|----------|-------------|--|--|
| UL YellowCard | E85371-251695 | | | | |
| Features | Block Copolymer | | | | |
| | Good Impact Resistance | | | | |
| | High Strength | | | | |
| | Low Temperature Impact Resistance | | | | |
| | | | | | |
| Uses | Blow Molding Applications | | | | |
| | Corrugated Sheet | | | | |
| | Food Packaging | | | | |
| | Industrial Applications | | | | |
| | Packaging | | | | |
| | Sheet | | | | |
| | | | | | |
| RoHS Compliance | RoHS Compliant | | | | |
| Processing Method | Blow Molding | | | | |
| | Sheet Extrusion | | | | |
| | Vacuum Forming | | | | |
| | | | | | |
| Physical | Nominal Value | Unit | Test Method | | |
| Specific Gravity | 0.900 | g/cm³ | ASTM D792 | | |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | 0.50 | | | | |
| kg) | 0.50 | g/10 min | ASTM D1238 | | |
| Mechanical | Nominal Value | Unit | Test Method | | |
| Tensile Strength (Yield) | 28.4 | MPa | ASTM D638 | | |
| Tensile Elongation (Break) | > 100 | % | ASTM D638 | | |
| Flexural Modulus | 1180 | MPa | ASTM D790 | | |
| Impact | Nominal Value | Unit | Test Method | | |
| Notched Izod Impact | | | ASTM D256 | | |
| -10°C | 44 | J/m | | | |
| 23°C | 490 | J/m | | | |
| Thermal | Nominal Value | Unit | Test Method | | |

| Deflection Temperature Under Load (0.45 | | | |
|---|---------------|----|-------------|
| MPa, Unannealed) | 100 | °C | ASTM D648 |
| | | | |
| Flammability | Nominal Value | | Test Method |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

