

# ADEKA EP-4010S

Epoxy; Epoxide  
Adeka Corporation

Message:  
Flexibility, low stress

General Information		
Features	Good Flexibility	
Physical	Nominal Value	Unit
Chlorine Content	0.3	wt%
Chlorine Content - Saponifiable	0.0200	wt%
Color - G	< 2.0	
Epoxy Equivalent	350 g/ep	
Thermoset	Nominal Value	Unit
Thermoset Mix Viscosity (25°C)	50000	cP

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT