

# Yuyao PP TL601

Polypropylene

Yuyao Tenglong Plastics Co., Ltd.

## Message:

Yuyao PP TL601 is a Polypropylene product. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PP TL601 include electrical/electronic applications, agricultural, appliances, handles and mining applications.

Characteristics include:

- Flame Rated
- Flame Retardant
- Heat Resistant
- Good Processability
- Halogen Free

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Heat Aging Resistance		
	Good Processability		
	Good Thermal Stability		
	Halogen Free		
Uses	Agricultural Applications		
	Appliance Components		
	Communication Applications		
	Connectors		
	Electrical Parts		
	Flexible Grips		
	Mining Applications		
	Switches		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.950	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	31.0	MPa	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638
Flexural Modulus	1000	MPa	ASTM D790
Flexural Strength	35.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	6.00	kJ/m <sup>2</sup>	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	120	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	V-2		
3.20 mm	V-2		
Injection	Nominal Value	Unit	
Drying Temperature	85.0 to 90.0	°C	
Drying Time	2.0 to 3.0	hr	
Processing (Melt) Temp	185 to 215	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	60.0 to 90.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

