

VITAMIDE® BS10VN6607

Polyamide 6
Jackdaw Polymers

Message:

VITAMIDE® BS10VN6607 is a Polyamide 6 (Nylon 6) product. It is available in Europe. Primary characteristic: flame rated.

General Information			
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792, ISO 1183
Water Absorption			
24 hr	2.6	%	ASTM D570
23°C, 24 hr	2.6	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			
Break	75.0	MPa	ISO 527-2
--	75.0	MPa	ASTM D638
Tensile Elongation (Break)	35	%	ASTM D638, ISO 527-2
Flexural Modulus	2800	MPa	ASTM D790, ISO 178
Flexural Strength	120	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength ¹	5.00	kJ/m ²	ASTM D256
Charpy Unnotched Impact Strength	No Break		ISO 179
Notched Izod Impact Strength	5.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	195	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	65.0	°C	ASTM D648, ISO 75-2/A
Melting Temperature	218	°C	ISO 1218, ASTM D2117
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	6.0E+15	ohms · cm	ASTM D257, IEC 60093
Dielectric Strength	13	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index			
Solution A	600	V	IEC 60112
--	600	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94
NOTE			
1.	Method B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

