HIFOR Xtreme® SC74858

Linear Low Density Polyethylene

Westlake Chemical Corporation

Message:

WESTLAKE HIFOR Wtreme SC74858 polymer is a high strength, good clarity linear low density polyethylene designed for blown film extrusion that contains no slip or antiblock and processing aid. Films produced with this resin exhibit an excellent toughness. Other features of this resin include good clarity and machine direction tear resistance.

General Information			
Features	Good Impact Resistance		
	Good Tear Strength		
	Good Toughness		
	High Strength		
	Medium Clarity		
Uses	Food Packaging		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.917	g/cm³	ASTM D4883
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	0.50	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Secant Modulus			
Secant Modulus			ASTM D882
1% Secant, MD	186	MPa	ASTM D882
	186 207	MPa MPa	ASTM D882
1% Secant, MD			ASTM D882 ASTM D882
1% Secant, MD 1% Secant, TD			
1% Secant, MD 1% Secant, TD Tensile Strength	207	MPa	
1% Secant, MD 1% Secant, TD Tensile Strength MD : Break	58.6	MPa MPa	
1% Secant, MD 1% Secant, TD Tensile Strength MD : Break TD : Break	58.6	MPa MPa	ASTM D882
1% Secant, MD 1% Secant, TD Tensile Strength MD : Break TD : Break Tensile Elongation	58.6 44.8	MPa MPa MPa	ASTM D882
1% Secant, MD 1% Secant, TD Tensile Strength MD : Break TD : Break Tensile Elongation MD : Break	58.6 44.8	MPa MPa MPa %	ASTM D882
1% Secant, MD 1% Secant, TD Tensile Strength MD : Break TD : Break Tensile Elongation MD : Break TD : Break	58.6 44.8 600 900	MPa MPa MPa %	ASTM D882 ASTM D882
1% Secant, MD 1% Secant, TD Tensile Strength MD : Break TD : Break Tensile Elongation MD : Break TD : Break Dart Drop Impact	207 58.6 44.8 600 900 750	MPa MPa MPa % % 96	ASTM D882 ASTM D882 ASTM D1709

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

