

RTP 4000 AR 10 TFE 10

Polyphthalamide

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
-Preliminary Product Data per RTP Co.-

General Information			
Filler / Reinforcement	Aramid fiber, 10% filler by weight		
Additive	PTFE lubricant (10%)		
Features	Lubrication		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.2	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.25	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5860	MPa	ASTM D638
Tensile Strength	68.9	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	4480	MPa	ASTM D790
Flexural Strength	131	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	27	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	270	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm, RTP Tested)	HB		UL 94
Additional Information			
Mold Shrinkage, Linear-Flow, ASTM D955, 0.25in.: 18mil/in.			
Injection	Nominal Value	Unit	
Rear Temperature	307 - 343	°C	
Middle Temperature	307 - 343	°C	

Front Temperature	307 - 343	°C
Mold Temperature	135 - 163	°C
Injection Pressure	68.9 - 124	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

