

Infino LS-3302A

Polycarbonate
SAMSUNG SDI CO., LTD.

Message:
Infino LS-3302A is a Polycarbonate (PC) product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

General Information			
UL YellowCard	E115797-100167836		
Filler / Reinforcement	Glass Fiber		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/10.0 kg)	25	g/10 min	ASTM D1238, ISO 1133
Ash Content	31	%	ISO 3451
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5700	MPa	ISO 527-2/50
Tensile Strength			
Yield ¹	98.0	MPa	ASTM D638
Yield	100	MPa	ISO 527-2/50
Break	106	MPa	ISO 527-2/50
Tensile Strain (Break)	3.0	%	ISO 527-2/50
Flexural Modulus			
-- ²	5800	MPa	ASTM D790
-- ³	5900	MPa	ISO 178
Flexural Strength			
-- ⁴	140	MPa	ASTM D790
-- ⁵	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁶ (23°C)	16	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	150	J/m	ASTM D256
23°C ⁷	12	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 4.00 mm	145	°C	ISO 75-2/B
0.45 MPa, Annealed	146	°C	ISO 75-2/B
1.8 MPa, Unannealed, 3.20 mm	140	°C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm	140	°C	ISO 75-2/A

1.8 MPa, Annealed, 4.00 mm	141	°C	ISO 75-2/A
Vicat Softening Temperature			
--	148	°C	ISO 306/B50
--	151	°C	ISO 306/B120
Injection	Nominal Value	Unit	
Drying Temperature			
--	100	°C	
Desiccant Dryer	100	°C	
Drying Time			
--	4.0 to 6.0	hr	
Desiccant Dryer	2.0 to 4.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	250 to 260	°C	
Middle Temperature	270 to 280	°C	
Front Temperature	290	°C	
Nozzle Temperature	290	°C	
Mold Temperature	80.0 to 120	°C	
Injection Pressure	98.1	MPa	
Back Pressure	0.490 to 1.96	MPa	
Screw Speed	50 to 150	rpm	
NOTE			
1.	5.0 mm/min		
2.	2.8 mm/min		
3.	2.0 mm/min		
4.	2.8 mm/min		
5.	2.0 mm/min		
6.	Thickness: 4 mm		
7.	Thickness: 4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT