

Tempalux® 30% GF

Polyether Imide
Westlake Plastics Company

Message:

An amorphous thermoplastic polyetherimide, stock shapes from ULTEM® resin possess a combination of useful characteristics, including high strength at elevated temperatures, high modulus, and broad chemical resistance. Tempalux stock shapes are inherently flame resistant with low smoke emission. Tempalux stock shapes display property retention and resistance to environmental stress cracking when exposed to a wide variety of chemicals. The standard color of Tempalux stock shapes is light amber. Glass filled grades appear tan or greenish in color. Tempalux rod, slab, and tubular bar are air annealed for stress relief.

Applications Include:

Burn-in test sockets

Connectors

Automotive components

Valves, electrical fittings

Advantages of Tempalux:

Inherent flame resistance

Extremely low NBS smoke evolution

Superior limiting oxygen index

Exceptional tensile and flexural strength

Broad chemical resistance

UV stable

FDA compliant

General Information	
Filler / Reinforcement	Glass Fiber,30% Filler by Weight
Features	Amorphous
	Flame Retardant
	Food Contact Acceptable
	Good Chemical Resistance
	Good UV Resistance
	High ESCR (Stress Crack Resist.)
	High Temperature Strength
	High Tensile Strength
Uses	Low Smoke Emission
	Automotive Applications
	Connectors
	Electrical Parts
	Valves/Valve Parts
Agency Ratings	FDA Unspecified Rating
Appearance	Green
	Tan
Forms	Film
	Rod

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792
Water Absorption (24 hr)	0.16	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	114		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8960	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	169	MPa	
Break	159	MPa	
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	8960	MPa	ASTM D790
Flexural Strength (Yield)	228	MPa	ASTM D790
Compressive Modulus	6470	MPa	ASTM D695
Compressive Strength	212	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Unnotched Izod Impact	430	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	212	°C	
1.8 MPa, Unannealed	210	°C	
CLTE - Flow	2.0E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.26	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	3.0E+16	ohms·cm	ASTM D257
Dielectric Strength	30	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	3.70		ASTM D150
Dissipation Factor (1 kHz)	1.5E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.406 mm)	V-0		UL 94
Oxygen Index	50	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

