

QR Resin QR-1220LG(V)

Polycarbonate + ABS

QTR, Inc.

Message:

QR Resin QR-1220LG(V) is a Polycarbonate + ABS (PC+ABS) product. It can be processed by injection molding and is available in North America.

Characteristics include:

- Flame Rated
- Good UV Resistance
- Impact Resistant
- Low Gloss

General Information			
Features	Good Impact Resistance		
	Good UV Resistance		
	Low Gloss		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	53.1	MPa	ASTM D638
Tensile Elongation (Break)	80	%	ASTM D638
Flexural Modulus	2210	MPa	ASTM D790
Flexural Strength (Yield)	84.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	530	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	124	°C	
1.8 MPa, Unannealed	107	°C	
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	104	°C	
Drying Time	3.0 to 4.0	hr	

Rear Temperature	249 to 282	°C
Middle Temperature	254 to 288	°C
Front Temperature	260 to 296	°C
Nozzle Temperature	271 to 296	°C
Processing (Melt) Temp	271 to 299	°C
Mold Temperature	60.0 to 82.2	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT