

PRIMALENE WPP04PET

Polyethylene Terephthalate

Southern Polymer, Inc.

Message:

Polyethylene Terephthalate (PET)

Applications:

Packaging

Features:

TPA-based

Uncrystallized amorphous copolymer

FDA 21 CFR 177.1630

General Information			
Features	Amorphous		
	Copolymer		
	Food Contact Acceptable		
Uses	Packaging		
Agency Ratings	FDA 21 CFR 177.1630		
Physical	Nominal Value	Unit	Test Method
Apparent Density	0.90	g/cm³	ASTM D1895
Water Absorption (Equilibrium)	< 0.20	%	ASTM D570
Color b	-6.00 to 0.00		
Color L	52.0 to 58.0		
Intrinsic Viscosity	0.61 to 0.65		
Black Specks	None		
Chip Size ¹	0.280 to 0.400		
Thermal	Nominal Value	Unit	
Peak Melting Temperature	> 240	°C	
NOTE			
1.	gm/20 chips		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT