

NORYL GTX™ GTX840 resin

Polyphenylene Ether + PS + Nylon

SABIC Innovative Plastics

Message:

40% glass filled PPE+PA66 blend for automotive under-the-hood and FLEN applications

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight		
Uses	Parts under the hood of a car		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm ³	ASTM D792, ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/5.0 kg)	10.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow: 3.20mm	0.24 - 0.27	%	Internal method
Transverse flow: 3.20mm	0.60 - 0.63	%	Internal method
Water Absorption			
Equilibrium, 23°C	0.30	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.10	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	13500	MPa	ASTM D638
--	13900	MPa	ISO 527-2/1
Tensile Strength			
Fracture ²	178	MPa	ASTM D638
Fracture	198	MPa	ISO 527-2/5
Tensile Elongation			
Fracture ³	2.0	%	ASTM D638
Fracture	2.0	%	ISO 527-2/5
Flexural Modulus			
50.0mm span ⁴	11900	MPa	ASTM D790
-- ⁵	12300	MPa	ISO 178
Flexural Stress			
--	280	MPa	ISO 178
Yield, 50.0mm span ⁶	249	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			

-30°C	11	kJ/m ²	ISO 179/2C
23°C ⁷	11	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	90	J/m	ASTM D256
23°C	94	J/m	ASTM D256
-30°C ⁸	11	kJ/m ²	ISO 180/1A
23°C ⁹	11	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 6.40mm	260	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ¹⁰	258	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 6.40mm	247	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹¹	244	°C	ISO 75-2/af
Vicat Softening Temperature	246	°C	ISO 306/B50, ISO 306/B120
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	1.6E-5 - 2.0E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	9.0E-5 - 9.4E-5	cm/cm/°C	ASTM E831
Injection	Nominal Value	Unit	
Drying Time, Maximum	8.0	hr	
Suggested Shot Size	30 - 50	%	
Back Pressure	0.345 - 1.38	MPa	
Screw Speed	20 - 100	rpm	
Vent Depth	0.013 - 0.038	mm	
Injection instructions			
Minimum Moisture Content: .02 %			
NOTE			
1.	5.0 mm/min		
2.	Type 1, 5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		
7.	80*10*4 sp=62mm		
8.	80*10*4		
9.	80*10*4		
10.	80*10*4 mm		
11.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

