# Centrene® HDF193B

## High Density (HMW) Polyethylene Qenos Pty Ltd

### Message:

Centrene® HDF193B is a black high molecular weight bimodal PE100 High Density Polyethylene. It is a high performance resin for use in pressure pipes where service life to 100 years is required. HDF193B offers a balance of excellent processing characteristics along with outstanding toughness, chemical resistance and slow crack growth resistance. HDF193B will also provide excellent resistance to the effects of ultra-violet light exposure in outdoor applications due to well dispersed carbon black.

Centrene® HDF193B is suitable for extrusion into a full range of pipes, where High Density, PE 100 type resins are required. In particular, a broad processing window and good sag resistance enables the extrusion of larger bore, thick wall pipe. HDF193B is suitable for use in the transport of a wide range of fluids for industrial, rural and mining applications, including potable water. Suitability for use in any application should be determined by appropriate performance testing.

General Information					
Additive	Carbon Black				
Features	Bimodal Molecular Weight Distribution				
	Good Chemical Resistance				
	Good Processability				
	Good UV Resistance				
	High Density				
	High ESCR (Stress Crack Resist.)				
	High Molecular Weight				
	Ultra High Toughness				
Uses	Fittings				
	Industrial Applications				
	Mining Applications				
	Outdoor Applications				
	Piping				
Agency Ratings	AS/NZS 4130				
	AS/NZS 4131				
Appearance	Black				
Processing Method	Pipe Extrusion				
Physical	Nominal Value	Unit	Test Method		
Density	0.956	g/cm³	Internal Method		
Melt Mass-Flow Rate (MFR)			ASTM D1238		
190°C/21.6 kg	8.9	g/10 min			
190°C/5.0 kg	0.30	g/10 min			
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D)	63		ASTM D2240		

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup> (1.90 mm)	1300	MPa	ASTM D638
Tensile Strength <sup>2</sup>			ASTM D638
Yield, 1.90 mm	26.0	MPa	
Break, 1.90 mm	33.0	MPa	
Tensile Elongation <sup>3</sup> (Break, 1.90 mm)	760	%	ASTM D638
Flexural Modulus - 1% Secant <sup>4</sup>	1150	MPa	ASTM D790
NOTE			
1.	Type IV, 50 mm/min		
2.	Type IV, 50 mm/min		
3.	Type IV, 50 mm/min		
4.	13 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

