

Reslen PPH 10/GWT 960 HF

Polypropylene Homopolymer
Polimarky Spolka Jawna

Message:

Reslen PPH 10/GWT 960 HF is a Polypropylene Homopolymer (PP Homopolymer) product. It is available in Europe.
Characteristics include:
Flame Retardant
Homopolymer

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Homopolymer		
Physical	Nominal Value	Unit	Test Method
Density	1.05 to 1.11	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0 to 20	g/10 min	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1400 to 1900	MPa	ISO 527-2
Tensile Stress	22.0 to 27.0	MPa	ISO 527-2
Tensile Strain (Break)	40 to 100	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.8 to 4.5	kJ/m²	ISO 179/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	55.0	°C	ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/A120
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	40.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

