

# CERTENE™ LLBF-120B

Linear Low Density Polyethylene  
Muehlstein

Message:

LLBF-120B is a certified prime resin containing Butene-comonomer, specially designed for production of Blown films for general purpose packaging. LLBF-120B features easy processability with very good film strength as well as wide heat sealing temperature range. LLBF-120B major applications include garment bags, produce bags and liners. Maximum recommended film drawdown is 0.5 mil. LLBF-120B contains no slip and medium antiblock.

General Information			
Additive	Moderate caking resistance		
Features	Low density		
	Workability, good		
	Good heat sealability		
	General		
	Moderate caking resistance		
Uses	Packaging		
	Films		
	Lining		
	Bags		
	General		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	
secant modulus			ASTM D882
1% secant, MD: 25 µm	215	MPa	ASTM D882
1% secant, TD: 25 µm	250	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 25 µm	12.0	MPa	ASTM D882
TD: Yield, 25 µm	11.0	MPa	ASTM D882
MD: Break, 25 µm	45.0	MPa	ASTM D882
TD: Break, 25 µm	30.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Break, 25 µm	650	%	ASTM D882
TD: Break, 25 µm	990	%	ASTM D882

Dart Drop Impact (25 µm)	85	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm	80	g	ASTM D1922
TD : 25 µm	550	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.4 µm)	65		ASTM D2457
Haze (25.4 µm)	7.3	%	ASTM D1003

#### Additional Information

This Specimen was compression molded and was tested according to ASTM D1928 Procedure C.

Extrusion	Nominal Value	Unit
Melt Temperature	200 - 220	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

