Novamid® 2430A

Polyamide 66/6 Copolymer

DSM Engineering Plastics

Message:

Novamid[®] 2430A is a Polyamide 66/6 Copolymer (Nylon 66/6) material. It is available in Asia Pacific for extrusion or film extrusion. Primary attribute of Novamid[®] 2430A: Flame Rated. Typical application of Novamid[®] 2430A: Film

Typical application of Novamid © 2450A. Tim

General Information	
Uses	Film
Processing Method	Extrusion
	Film Extrusion

Physical	Nominal Value	Unit	Test Method		
Density	1.14	g/cm³	ISO 1183		
Water Absorption (Equilibrium, 23°C, 50%					
RH)	3.5	%	ISO 62		
Viscosity Number	246	cm³/g	ISO 307		
Thermal	Nominal Value	Unit	Test Method		
Melting Temperature	193	°C	ISO 11357-3		
Flammability	Nominal Value		Test Method		
Flammability Classification (1.50 mm)	НВ		IEC 60695-11-10, -20		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

