

Kotex KGN-30MRA

Polycarbonate
Kotec Corporation

Message:

Kotex KGN-30MRA is a Polycarbonate (PC) product filled with 30% glass fiber. It is available in Asia Pacific or Europe.
Characteristics include:
Flame Rated
Flame Retardant
Good Mold Release
High Viscosity
Mold Release Agent

General Information			
UL YellowCard	E146413-223410		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Flame Retardant		
	Mold Release		
Features	Flame Retardant		
	Good Mold Release		
	High Viscosity		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	< 0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	127	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	7550	MPa	ASTM D790
Flexural Strength	162	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	100	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	146	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength (1.60 mm)	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.20		ASTM D150

Dissipation Factor (1 MHz)	8.0E-3		ASTM D150
Arc Resistance	110	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.70 mm)	V-0		UL 94
Optical	Nominal Value		Test Method
Haze (3.00 mm)	Translucent		ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

