

HiFill® PEEK CF30 A NAT

Polyetheretherketone

Techmer Engineered Solutions

Message:

HiFill® PEEK CF30 A NAT is a Polyetheretherketone (PEEK) product filled with carbon fiber. It can be processed by injection molding and is available in North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Carbon Fiber		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10	%	ASTM D955
Water Absorption (24 hr)	0.040	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	262	MPa	ASTM D638
Tensile Elongation (Break)	1.7	%	ASTM D638
Flexural Modulus	22800	MPa	ASTM D790
Flexural Strength	379	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	335	°C	ASTM D648
CLTE - Flow	1.1E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+3	ohms	ASTM D257
Volume Resistivity	1.0E+2 to 1.0E+3	ohms · cm	ASTM D257
Shielding Effectiveness - 30 to 1000 MHz	30	dB	ASTM D4935
Static Decay	< 0.500		FTMS 101B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	249	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	360 to 388	°C	
Middle Temperature	360 to 388	°C	
Front Temperature	360 to 388	°C	
Processing (Melt) Temp	360 to 382	°C	
Mold Temperature	177 to 218	°C	

Back Pressure	0.345 to 0.689	MPa
Screw Speed	50 to 100	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

