

Hostacom ERC 213N C12360

Polypropylene Copolymer
LyondellBasell Industries

Message:

Hostacom ERC 213N is a UV stabilised, 15 % mineral filled polypropylene copolymer for injection moulding. It combines a good flowability with excellent stiffness/impact properties. The grade has been specifically designed for interior trim applications with higher impact and scratch resistance requirements.

General Information			
Filler / Reinforcement	Mineral,15% Filler by Weight		
Features	Copolymer		
	Good Flow		
	Good Processability		
	Good Surface Finish		
	High Impact Resistance		
	Medium Gloss		
	Scratch Resistant		
Uses	Automotive Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	19.0	MPa	ISO 527-2/50
Flexural Modulus - Secant	1650	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-40°C	3.0	kJ/m ²	
23°C	25	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	95.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

