

CYCOLAC™ INP564 resin

Acrylonitrile Butadiene Styrene + SAN

SABIC Innovative Plastics

Message:

SABIC INP564 provides compatibility with a wider range of ABS grades than many color concentrate bases; allows better dispersion than pellets; allows concentrate manufacturers to produce both pelletized and dry blend concentrate; provides a base resin with less heat history than pellets; suitable for direct weather exposure; can be used in all SAN applications where a fine particle size is desired

General Information			
Features	Good weather resistance		
Uses	Color masterbatch		
RoHS Compliance	RoHS compliance		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.08	g/cm ³	ASTM D792
--	1.07	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			
230°C/3.8 kg	38	g/10 min	ASTM D1238
220°C/10.0 kg	78	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	123		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3890	MPa	ASTM D638
--	3840	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	52.0	MPa	ASTM D638
Yield	54.1	MPa	ISO 527-2/50
Fracture ³	53.6	MPa	ASTM D638
Fracture	54.1	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	1.6	%	ASTM D638
Yield	1.2	%	ISO 527-2/50
Fracture ⁵	1.7	%	ASTM D638
Fracture	1.2	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	3720	MPa	ASTM D790
-- ⁷	3460	MPa	ISO 178
Flexural Stress			
--	65.4	MPa	ISO 178
Yield, 50.0mm span ⁸	82.5	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	1.1	kJ/m ²	ISO 179/2C
Notched Izod Impact			
-30°C	22	J/m	ASTM D256
23°C	14	J/m	ASTM D256
-30°C ⁹	2.5	kJ/m ²	ISO 180/1A
23°C ¹⁰	1.9	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	95.2	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	83.4	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹¹	85.3	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	102	°C	ISO 306/B50
--	104	°C	ISO 306/B120
NOTE			
1.	5.0 mm/min		
2.	Type 1, 5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	Type 1, 5.0 mm/min		
5.	Type 1, 5.0 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*4		
10.	80*10*4		
11.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT