

Zytel® HTN 53G50HSLR NC010

HIGH PERFORMANCE POLYAMIDE RESIN

DuPont Performance Polymers

Message:

50% Glass Reinforced High Performance Polyamide with Improved Impact and Stiffness

General Information				
UL YellowCard		E41938-234510		
Filler / Reinforcement		Glass Fiber,50% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Agency Ratings		UL Unspecified Rating		
Processing Method		Injection Molding		
Multi-Point Data		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
Part Marking Code (ISO 11469)		>PA-GF50<		
Part Marking Code (SAE J1344)		>PA-GF50<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.59	--	g/cm³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.40	--	%	
Flow	0.20	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	16500	16300	MPa	ISO 527-2
Tensile Stress (Break)	250	215	MPa	ISO 527-2
Tensile Strain (Break)	2.8	3.1	%	ISO 527-2
Flexural Modulus	15000	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°C	14	--	kJ/m²	
23°C	15	--	kJ/m²	
Charpy Unnotched Impact Strength (23°C)	95	--	kJ/m²	ISO 179/1eU
Notched Izod Impact Strength				ISO 180/1A
-40°C	14	--	kJ/m²	
23°C	15	--	kJ/m²	
Thermal	Dry	Conditioned	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	236	--	°C	ISO 75-2/A
Melting Temperature ¹	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.4E-5	--	cm/cm/°C	
Flow : -40 to 23°C	1.7E-5	--	cm/cm/°C	
Transverse	5.5E-5	--	cm/cm/°C	
Transverse : -40 to 23°C	5.5E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	--	ohms·cm	IEC 60093
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (1.00 mm)	25	--	mm/min	ISO 3795
Flammability Classification				IEC 60695-11-10, -20
0.750 mm	HB	--		
1.50 mm	HB	--		
Oxygen Index	27	--	%	ISO 4589-2
NOTE				

1. First Heat

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT