

Precision Polymer E60H

Ethylene Propylene Diene Terpolymer

Precision Polymer Engineering Ltd.

Message:

Sulphur cured, off-white Ethylene Propylene Terpolymer, 55-65 °IRHD. Terpolymer of ethylene, propylene and diene monomers. Formulated using only those ingredients determined by the United States Federal Food and Drug Administration (FDA) to be in accordance with Code of Federal Regulations Title (CFR21), Section 177.2600. Extraction tested in distilled water.
Suitable for repeated use with dry and aqueous foodstuffs intended for human consumption. Not suitable for use with fatty foodstuffs.

General Information			
Features	Compliance of Food Exposure		
Agency Ratings	FDA 21 CFR 177.2600		
Appearance	White-like		
Hardness	Nominal Value	Test Method	
IRHD Hardness	60	ASTM D1415, ISO 48	
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	13.8	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	250	%	ASTM D412, ISO 37
Compression Set			
100°C, 24 hr	64	%	ASTM D395B
100°C, 24 hr ¹	64	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (125°C, 168 hr)	-20	%	ASTM D412, ISO 37
Change in Ultimate Elongation in Air (125°C, 168 hr)	-20	%	ASTM D412, ISO 37
Change in IRHD Hardness in Air (125°C, 168 hr)	15		ASTM D573, ISO 188
Thermal	Nominal Value	Unit	
Maximum Operating Temperature	150	°C	
Low Temperature Resistance - Non-brittle for 3 minutes			
--	-45	°C	ISO R812
--	-45	°C	ASTM D2137
Additional Information	Nominal Value	Unit	Test Method
Minimum Operating Temperature: -40°C (-40°F)			
NOTE			
1.	Type B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

