

# Chemlon® 66GF8

Polyamide 66

Teknor Apex Company (Chem Polymer)

## Message:

66GF8 is a 40% glass fibre reinforced nylon 66 that offers excellent mechanical performance coupled with good surface finish and flow.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 40% filler by weight		
Features		Good liquidity		
		Excellent appearance		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.46	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>1</sup>	0.30 - 0.80	--	%	Internal method
Water Absorption (Equilibrium, 23°C, 50% RH)	1.5	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10500	8000	MPa	ISO 527-2
Tensile Stress	190	145	MPa	ISO 527-2
Tensile Strain (Break)	3.0	--	%	ISO 527-2
Flexural Modulus	10000	5900	MPa	ISO 178
Flexural Stress	275	160	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	10	30	kJ/m <sup>2</sup>	ISO 180/A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	> 240	--	°C	ISO 75-2/B
1.8 MPa, not annealed	> 240	--	°C	ISO 75-2/A
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+16	1.0E+13	ohms · cm	IEC 60093
Dielectric Strength (3.00 mm)	15	--	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.50 mm, Teknor Apex test result)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	80.0		°C	

Drying Time	2.0	hr
Rear Temperature	270 - 290	°C
Middle Temperature	270 - 290	°C
Front Temperature	270 - 290	°C
Processing (Melt) Temp	270 - 290	°C
Mold Temperature	80.0 - 90.0	°C
Injection Rate	Fast	
Back Pressure	Low	
Screw Speed	Moderate	

#### Injection instructions

No drying is necessary unless the material has been exposed to air for longer than three hours. The appearance of splash marks on the surface of mouldings indicates excessive moisture is present.

#### NOTE


1. Mould shrinkage is significantly influenced by many factors including wall thickness, gating, moulding shape and processing conditions. The range values given are determined from specimen bar mouldings of 1.5mm to 4mm wall thickness. They are provided as a guide for comparison purposes only and no guarantee should be inferred from their inclusion. (Specimens measured in the dry state, 24 hours after moulding).

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT