

Polifor® C 30 TE/40 BIANCO 0330

Polypropylene Copolymer

SO.F.TER. SPA

Message:

Polypropylene copolymer, 42% mineral filled

General Information			
Filler / Reinforcement	Mineral,42% Filler by Weight		
Features	Copolymer		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	White		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage	1.0	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	28.0	MPa	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638
Flexural Modulus	2100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	45	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	55.0	°C	ASTM D648
Vicat Softening Temperature	78.0	°C	ASTM D1525 ¹
Flammability	Nominal Value	Test Method	
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Rear Temperature	190	°C	
Middle Temperature	210	°C	
Front Temperature	230	°C	
Mold Temperature	40.0 to 60.0	°C	
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

