

# WPP PP PPC3GF1.5-Black

Polypropylene Copolymer  
Washington Penn Plastic Co. Inc.

Message:  
Properties shown below for this filled blend are typical for a15% fiberglass reinforced polypropylene copolymer.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Additive	UV stabilizer		
Features	Rigid, good		
	High tensile strength		
	Copolymer		
	Good UV resistance		
	Medium liquidity		
Appearance	Black		
	Available colors		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.982	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	33.8	MPa	ASTM D638
Flexural Modulus <sup>2</sup>	1570	MPa	ASTM D790
Flexural Strength <sup>3</sup>	46.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	210	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	147	°C	ASTM D648
1.8 MPa, not annealed	87.0	°C	ASTM D648
Additional Information			
Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relativehumidity unless otherwise noted			
NOTE			
1.	51 mm/min		
2.	5.3 mm/min		
3.	5.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

