

# Rotolon 100

Polytetrafluoroethylene

Greene, Tweed & Co.

## Message:

This product is only available as a finished part, please contact Green, Tweed & Co. to discuss part availability, 215-216-9521.

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Molybdenum Disulfide Lubricant		
Features	Good Thermal Stability		
	Good Wear Resistance		
	Lubricated		
Uses	Seals		
Forms	Pellets		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	22.1	MPa	ASTM D638
Tensile Elongation (Yield)	370	%	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT