

RTP ESD A 100

Polypropylene
RTP Company

Message:

ESD Protection - Static Dissipative - Standard (Low) MFR

General Information			
Features	ESD Protection		
	Low Flow		
	Statically Conductive		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.970	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.50 to 2.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	1.2 to 1.7	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1030	MPa	ASTM D638
Tensile Strength	17.2	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	827	MPa	ASTM D790
Flexural Strength	24.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	No Break		ASTM D256
Unnotched Izod Impact (3.20 mm)	No Break		ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			
--	1.0E+5 to 9.9E+11	ohms	ASTM D257
--	1.0E+4 to 9.9E+10	ohms	ESD STM11.11
Volume Resistivity	1.0E+3 to 9.9E+9	ohms·cm	ASTM D257
Static Decay ¹	< 2.0	sec	FTMS 101C 4046.1
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	191 to 232	°C	
Mold Temperature	32.2 to 65.6	°C	
Injection Pressure	68.9 to 103	MPa	
NOTE			

1.

MIL-PRF-81705D, 5kV to 50 V, 12%
RH

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

