ELASTOSIL® LR 3040/50 A/B

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, LSR

Molded Parts, Food Contact, Plastics and Rubber Processing Molded Parts, Technical, Plastics and Rubber Processing Molded Parts, Automotive, Plastics and Rubber Processing

General Information			
Features	Fast Cure Food Contact Acceptable		
	Good Tear Strength		
Uses	Automotive Applications		
	Automotive Under the Hood		
	Gaskets		
	Membranes		
	Pacifiers		
	Seals		
	Valves/Valve Parts		
Processing Method	Injection Molding		
	Liquid Injection Molding (LIM)		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.12	g/cm³	ISO 1183
Viscosity	450	Pa·s	DIN 53019
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	49		DIN 53505
Tensile Strength	9.00	MPa	DIN 53504
Tensile Elongation at Break	480	%	DIN 53504
Compression Set	11	%	DIN ISO 815-B
Tear Strength			
	10.0	kN/m	ISO 34

40.0 kN/m **Rebound Resilience** 67 %

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

ASTM D624B

DIN 53512

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

