

SABIC® LDPE 2200H0

Low Density Polyethylene

Saudi Basic Industries Corporation (SABIC)

Message:

Description

SABIC® LDPE 2200H0 is a grade with a low melt flow range and contains no additives. This grade has a good draw down ability and very good optical properties.

Application

SABIC® LDPE 2200H0 is typically used for thin film applications combining high strength and good optical properties.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

General Information			
Features	Low density		
	High strength		
	Optical		
	Good stripping		
	Low liquidity		
Uses	Blown Film		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.33	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (Blown Film)	1.0		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Tensile Modulus			ISO 527-3
MD: 50 µm, blown film	190	MPa	ISO 527-3
TD: 50 µm, blown film	190	MPa	ISO 527-3
Tensile Stress			ISO 527-3
MD: Yield, 50 µm, blown film	11.0	MPa	ISO 527-3
TD: Yield, 50 µm, blown film	11.0	MPa	ISO 527-3
MD: Broken, 50 µm, blown film	27.0	MPa	ISO 527-3
TD: Broken, 50 µm, blown film	22.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Broken, 50 µm, blown film	> 200	%	ISO 527-3
TD: Broken, 50 µm, blown film	> 500	%	ISO 527-3
Impact	Nominal Value	Unit	Test Method
Impact Strength - Blown Film (50.0 µm)	300	J/cm	ASTM D4272
Blocking - Blown Film (50.0 µm)	30	g	Internal method

Re-blocking - Blown Film (50.0 µm)	10	g	Internal method
Tear Strength ¹			ISO 6383-2
MD : 50.0 µm	35.0	kN/m	ISO 6383-2
TD : 50.0 µm	40.0	kN/m	ISO 6383-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	98.0	°C	ISO 306/A
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 50.0 µm, Blown Film)	57		ASTM D2457
Haze (50.0 µm, Blown Film)	8.0	%	ASTM D1003A
Additional Information	Nominal Value	Unit	Test Method
Film properties have been measured at film of 50 µm with a BUR of 3.The film has been produced on Kiefel IBC blown film line with 200 kg/h. Die size 200 mm, die gap 0.8 mm.			
NOTE			

1. Blown Film

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

