

MACOMASS PP MM-PP BI 81 Copolymer

Polypropylene Copolymer

MACOMASS Verkaufs AG

Message:

MACOMASS PP MM-PP BI 81 Copolymer is a Polypropylene Copolymer (PP Copolymer) material. It is available in Europe.

Important attributes of MACOMASS PP MM-PP BI 81 Copolymer are:

- Flame Rated
- Copolymer
- Flame Retardant

General Information			
Features	Copolymer		
	Flame Retardant		
	Halogenated		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.920 to 0.960	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0 to 14	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	70.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	20.0	MPa	ISO 527-2
Tensile Strain (Break)	150	%	ISO 527-2
Flexural Modulus	1200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	86.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	53.0	°C	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-2		
3.20 mm	V-2		
Glow Wire Ignition Temperature			VDE 0471/2
1.60 mm	960	°C	
3.20 mm	960	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

