

Electrafil® PC 04007

Polycarbonate

Techmer Engineered Solutions

Message:

Electrafil® PC 04007 is a polycarbonate (PC) product. It can be processed by injection molding and is available in North America.

Features include:

flame retardant/rated flame

Electromagnetic shielding (EMI)

General Information			
Features	Electromagnetic shielding (EMI)		
Appearance	Available colors		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	62.1	MPa	ASTM D638
Tensile Elongation (Break)	4.6	%	ASTM D638
Flexural Modulus	2480	MPa	ASTM D790
Flexural Strength	104	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	120	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.18 mm)	440	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	129	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0 - 1.0E+3	ohms	ASTM D257
Volume Resistivity	1.0 - 1.0E+3	ohms · cm	ASTM D257
Static Decay			FTMS 101B
Shielding Effectiveness - 30 to 1000 MHz	50	dB	ASTM D4935
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.18 mm)	V-1		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.10	%	
Rear Temperature	302 - 316	°C	
Middle Temperature	316 - 332	°C	

Front Temperature	310 - 327	°C
Nozzle Temperature	310 - 327	°C
Processing (Melt) Temp	304 - 327	°C
Mold Temperature	71.1 - 87.8	°C
Injection Rate	Moderate	
Back Pressure	0.00 - 0.689	MPa

Injection instructions

Screw Speed: MediumRecommendations for Molding and Tool Conditions: Well vented moldMoisture Content, as received: Product is packaged at 0.2% or less.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

