

MIRASON™ 68

Low Density Polyethylene

Mitsui Chemicals, Inc.

Message:

MIRASON™ 68 is a Low Density Polyethylene material. It is available in Asia Pacific for injection molding. Primary attribute of MIRASON™ 68: Good Flexibility.

Typical applications include:

Caps/Lids/Closures

Engineering/Industrial Parts

General Information			
Features	Good Flexibility		
	Good Flow		
Uses	Closures		
	Industrial Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.916	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	23	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	49		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	8.83	MPa	
Break	11.8	MPa	
Tensile Elongation (Break)	500	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ASTM D746
Vicat Softening Temperature	84.0	°C	ASTM D1525
Melting Temperature	105	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

