

Durethan® BKV 15 DUS008 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 15 % glass fibers, injection molding

General Information				
UL YellowCard		E245249-100868026		
Filler / Reinforcement		Glass fiber reinforced material, 15% filler by weight		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.23	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.59	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.16	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.35	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.13	--	%	ISO 2577
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	6500	3100	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	130	65.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	12	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	5500	3100	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	180	80.0	MPa	ISO 178/A
23°C ⁶	205	110	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	5.3	8.0	%	ISO 178/A
ISO Shortname	PA 6, GR, 14-060, GF15	--		ISO 1874
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	45	45	kJ/m ²	ISO 179/1eU
23°C	50	100	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	< 10	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	40	40	kJ/m ²	ISO 180/1U

23°C	45	85	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Peak Force (23°C)	940	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	215	--	°C	ISO 75-2/B
1.8 MPa, not annealed	195	--	°C	ISO 75-2/A
Vicat Softening Temperature	210	--	°C	ISO 306/B120
Melting Temperature ⁸	220	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	3.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.0E-4	--	cm/cm/°C	ISO 11359-2
Injection	Dry	Unit		
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	260 - 290		°C	
Mold Temperature	80.0 - 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT