

# Osterlene® LLM1416

Linear Low Density Polyethylene

Osterman & Company

Message:

LLM1416 is best suited for applications requiring excellent clarity, gloss, toughness and heat seal. Typical blown film applications include; seal layer in coextrusions, heavy duty packaging and clarity packaging.

Osterlene LLM1416 meets the requirements of the Food and Drug Administration, 21 CFR Section 177.1520. This regulation allows the use of this olefin polymer in

"...articles or components of articles intended for use in contact with food." Specific limitations may apply. Contact your Osterman sales representative for more information.

General Information			
Additive	Processing aid		
Features	Highlight		
	Definition, high		
	Good toughness		
Uses	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Physical	Nominal Value	Unit	Test Method
Density	0.916	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.4	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction	> 1.0		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Puncture Energy	7.50	J	ASTM D3763
Film Puncture Force	82.7	N	ASTM D3763
secant modulus			ASTM D882
1% secant, MD	152	MPa	ASTM D882
1% secant, TD	157	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield	11.7	MPa	ASTM D882
TD: Yield	10.0	MPa	ASTM D882
MD: Fracture	69.6	MPa	ASTM D882
TD: Fracture	52.4	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	520	%	ASTM D882
TD: Fracture	600	%	ASTM D882
Elmendorf Tear Strength			ASTM D1922
MD	240	g	ASTM D1922

TD	420	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (60°)	130		ASTM D2457
Haze	4.0	%	ASTM D1003
Additional Information	Nominal Value	Unit	Test Method
Dart Impact	> 308.9	kN/m	ASTM D1709
Sealing Initial Temperature	100	°C	ASTM F88

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

